

USSN: 09/734,101
Atty. Docket No.: 10244
Amdt. dated August 6, 2004
Reply to Office Action of May 6, 2004

Amendments To The Claims

This listing of claims will replace all prior versions, and listings, of claims in the application:

Listing Of Claims:

Claim 1 (previously presented): A biaxially oriented film for ink jet printing, said film being ink-absorbing and said film having a water-wettable surface, said film comprising a porous high density polyethylene HDPE surface layer and a coating consisting essentially of a silicone glycol composition impregnated in the pore space of said surface layer, and said porous surface layer further comprising a printed image on an outer surface thereof.

Claim 2 (original): A biaxially oriented film according to claim 1, wherein said porous surface layer comprises: (i) a matrix comprising HDPE and (ii) a network of interconnecting pores communicating throughout said porous surface layer.

Claim 3 (previously presented): A biaxially oriented film according to claim 2, wherein said porous surface layer further comprises a cavitating agent.

Claim 4 (original): A biaxially oriented film according to claim 3, wherein said cavitating agent is calcium carbonate.

Claim 5 (original): A biaxially oriented film according to claim 1, further comprising a core layer co-extruded with said porous surface layer.

Claim 6 (original): A biaxially oriented film according to claim 5, wherein said core layer is a porous layer comprising (i) a matrix comprising HDPE; (ii) a network of interconnecting pores communicating throughout the porous core layer; and (iii) a cavitating agent.

Claim 7 (original): A biaxially oriented film according to claim 6, wherein the cavitating agent of said core layer is calcium carbonate.

USSN: 09/734,101
Atty. Docket No.: 10244
Amdt. dated August 6, 2004
Reply to Office Action of May 6, 2004

Claim 8 (original): A biaxially oriented film according to claim 7, further comprising a noncavitated skin layer coextruded to said core layer on the opposite side of the core layer from said porous high density polyethylene HDPE surface layer.

Claim 9 (previously presented): A biaxially oriented film according to claim 1, wherein the porous high density polyethylene HDPE surface layer is substantially free of high molecular weight polyethylene.

Claim 10 (previously presented): A biaxially oriented film according to claim 1, wherein the porous HDPE surface layer has an average pore diameter of 0.1 to 10 microns.

Claims 11-20 (canceled).